

	302	304	316	440	Alum	Titanium	Hastelloy C	Bronze	Brass	Cast Iron	Carbon Steel	PVDF	PVC	Tygon	ETFE	Noryl	Polyacetal	Nylon	ABS	PE	PP	Ryton	Carbon	Ceramic	Ceramagnet	Viton	BUNA N	Silicon	Neoprene	EPDM	Rubber	Epoxy	
Acetaldehyde ₅	A	A	A	-	B	A	A	D	-	-	C	-	D	D	A	-	A	A	D	C	B	A	A	A	-	D	B	B	D	B	C	A	
Acetamide	-	B	A	-	-	-	-	-	-	-	C	-	-	-	-	-	B	-	-	-	-	-	-	A	-	A	A	-	A	A	D	A	
Acetate Solv. 2	A	B	A	B	B	A	-	A	C	B	A	-	B	D	A	-	-	A	D	B	D	-	A	A	-	D	D	-	D	-	A		
Acetic Acid, Glacia ₁	-	B	A	A	B	A	A	C	C	D	A	-	C	B	A	C	D	D	D	B	B	A	A	A	-	D	D	B	C	B	C	B	
Acetic Acid 20%	-	B	A	-	-	A	A	-	C	-	-	A	B	-	A	A	-	D	-	-	A	A	-	A	-	A	C	-	C	-	-	B	
Acetic Acid 80%	-	B	A	-	-	A	A	-	C	-	-	A	D	-	A	B	-	D	-	-	B	-	-	A	-	A	C	-	D	-	-	B	
Acetic Acid	-	B	A	B	B	A	A	C	C	D	C	B	A	B	A	A	D	D	C	B	A	A	A	A	-	C	C	-	C	B	C	A	
Acetic Anhydride	B	A	A	B	B	A	A	C	D	B	D	D	D	D	A	D	D	D	D	C	B	A	A	A	-	D	A	C	B	C	B	C	A
Acetone ₅	A	A	A	B	B	A	A	A	A	A	A	D	D	D	A	D	B	A	D	C	B	A	A	A	A	D	D	B	C	A	D	B	
Acetyl Chloride	-	C	A	-	-	-	-	D	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	A
Acetylene ₂	A	A	A	A	A	B	-	B	-	A	A	-	B	-	-	-	A	A	-	-	D	A	A	A	-	A	A	C	B	A	C	A	
Acrylonitrile	A	A	C	-	B	B	B	A	-	C	-	-	-	-	-	-	B	-	D	-	B	A	A	A	-	C	D	-	D	-	-	A	
Alcohols																																	
Amyl	A	A	A	-	C	A	A	A	B	C	C	A	A	B	A	C	A	A	B	B	B	A	A	A	-	A	A	D	A	A	C	A	
Benzyl	-	A	A	-	B	A	A	A	C	-	-	-	D	B	-	A	A	A	D	D	A	-	A	A	-	A	D	-	B	B	D	A	
Butyl	A	A	A	-	B	B	A	B	C	C	C	A	A	B	A	A	A	-	B	B	A	A	A	-	A	A	D	A	A	A	A		
Diacetone ₂	-	A	A	-	A	A	A	C	-	A	-	D	-	-	A	A	A	A	-	-	D	-	A	A	-	D	D	-	D	A	D	A	
Ethyl	-	A	A	A	B	A	A	A	C	A	A	-	A	C	-	A	B	A	B	B	A	-	A	A	A	A	A	B	A	B	A	A	
Hexyl	-	A	A	-	A	A	A	A	C	-	A	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A	A	D	B	A	A	A	
Isobutyl	-	A	A	-	B	A	A	A	C	-	A	-	-	-	-	A	A	A	B	-	A	-	A	A	-	A	C	B	A	A	A	A	
Isopropyl	-	A	A	-	B	A	A	A	C	C	A	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A	C	C	B	A	A	A	
Methyl ₆	-	A	A	A	B	B	A	A	A	C	A	A	-	B	-	A	A	C	A	D	B	A	-	A	A	C	B	-	A	A	A	A	
Octyl	-	A	A	-	A	A	A	A	C	-	A	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	B	-	B	A	C	A	
Propyl	-	A	A	-	A	A	A	A	-	-	A	B	A	-	A	A	A	A	-	-	A	-	A	A	-	A	A	B	A	A	A	A	
Aluminum Chloride 20%	-	D	C	D	B	A	A	D	-	D	A	-	A	B	-	A	C	A	-	B	A	A	A	-	A	A	-	A	A	A	A	A	
Aluminum Chloride	C	D	C	-	D	C	A	C	-	D	B	A	A	A	A	A	-	D	-	-	A	A	A	-	A	A	C	A	-	-	-	A	
Aluminum Fluoride	-	D	C	D	-	D	B	-	-	-	A	A	A	-	A	A	C	D	-	B	A	-	A	-	A	A	C	A	-	-	C	A	
Aluminum Hydroxide6	-	A	A	A	A	-	-	A	-	D	A	-	A	-	A	A	B	A	-	-	A	-	A	A	A	A	A	-	A	-	-	A	A
Alum Potassium Sulfate (Alum), 10%	-	A	-	-	A	-	B	-	-	D	A	-	A	-	A	-	-	A	-	A	-	-	A	A	-	A	-	-	A	-	-	A	A
Alum Potassium Sulfate (Alum), 100%	-	D	A	B	B	-	B	C	-	-	A	-	A	B	A	A	C	D	-	B	A	-	A	A	-	A	A	-	A	-	-	A	A
Aluminum Sulfate	-	C	C	A	A	A	A	C	C	D	A	A	A	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A	A
Amines	A	A	A	-	A	B	A	B	-	A	B	-	C	A	A	B	D	A	-	-	-	-	A	A	-	D	D	C	B	B	C	A	
Ammonia 10%	-	-	A	-	-	A	A	-	-	-	-	D	A	-	A	A	-	A	-	-	A	A	-	A	-	A	D	-	A	-	-	B	
Ammonia, Anhydrous	A	B	A	A	B	B	A	D	-	D	B	D	A	B	A	A	D	A	-	B	A	B	C	A	-	D	B	B	A	A	D	A	
Ammonia, Liquids	-	A	A	A	D	-	B	D	-	A	A	-	A	B	A	A	D	-	-	D	A	-	A	A	-	D	B	B	A	A	D	A	
Ammonia, Nitrate	-	A	A	A	C	-	-	D	-	-	A	-	B	B	-	A	C	-	-	-	A	-	A	A	-	A	-	-	C	-	-	A	
Ammonium Bifluoride	-	C	A	-	D	-	B	-	-	-	-	-	A	-	-	A	D	-	-	-	A	-	-	A	-	A	A	-	-	-	-	A	
Ammonium Carbonate	B	A	A	A	C	A	B	B	-	C	B	-	A	B	A	A	D	A	-	-	A	-	A	A	-	B	D	C	A	A	-	A	
Ammonium Casenite	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	A	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A
Ammonium Chloride	C	A	C	A	C	D	A	D	C	D	D	A	A	B	A	A	B	A	-	B	A	A	A	-	A	A	C	A	A	A	A	A	
Ammonium Hydroxide	A	A	A	A	C	A	A	D	D	A	C	-	A	B	A	A	D	A	B	B	A	A	A	A	-	B	B	B	A	A	C	A	
Ammonium Nitrate	A	A	A	A	B	A	A	D	D	A	D	-	A	B	A	A	C	D	-	B	A	A	A	-	D	A	C	A	A	A	A	A	
Ammonium Oxalate	-	A	A	A	-	-	A	-	-	-	A	-	-	-	-	-	B	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A
Ammonium Persulfate	-	A	A	A	C	C	A	A	-	D	A	D	A	-	A	A	D	D	-	-	A	-	A	A	-	C	A	-	-	-	-	-	A
Ammonium Phosphate, Dibasic	B	A	A	A	B	A	A	C	-	-	D	-	A	-	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	
Ammonium Phosphate, Monobasic	-	A	A	A	B	A	A	C	-	-	A	-	A	A	A	B	A	-	B	A	-	B	A	-	A	A	B	A	A	A	A	A	
Ammonium Phosphate, Tribasic	B	A	A	A	B	A	A	C	-	C	D	-	A	-	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	
Ammonium Sulfate	C	D	B	A	B	A	A	B	C	C	C	A	A	D	A	B	D	-	B	A	A	A	A	-	D	A	B	A	A	A	A		
Ammonium Thio-Sulfate	-	-	A	-	-	A	-	-	D	A	-	-	-	-	-	B	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A
Amyl-Acetate	B	A	A	C	B	A	A	C	-	-	C	C	D	D	A	D	A	B	-	D	D	A	A	A	-	D	D	D	D	A	D	A	
Amyl Alcohol	-	A	A	-	B	A	A	A	-	-	A	A	A	B	A	C	A	A	-	B	A	-	A	A	-	B	B	D	A	A	C	A	
Amyl Chloride	-	C	B	-	D	-	A	A	-	-	A	A	D	C	A	D	A	C	-	D	D	-	A	A	-	A	D	-	D	D	D	A	
Aniline	B	A	A	A	C	A	B	C	-	-	C	C	D	D	A	D	D	C	D	C	B	A	A	A	-	C	D	C	D	B	D	A	
Anti-Freeze	-	A	A	-	A	-	A	B	B	B	C	-	A	B	A	A	A	A	B	B	A	A	A	A	-	A	A	C	A	A	A	A	
Antimony Trichloride	-	D	D	-	D	C	A	-	-	-	-	-	A	A	A	-	-	D	-	A	-	-	A	-	A	-	-	C	-	-	-	A	
Aqua Regia (80% HCl, 20% HNO)	-	D	D	-	D	A	D	D	-	-	-	C	D	D	A	D	D	D	-	D	C	-	-	D	-	C	D	C	D	D	D	D	
Arochlor 1248	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	-	-	-	-	-	-	-	-	-	A	D	-	D	B	D	A	
Aromatic Hydrocarbons	-	-	A	-	A	-	-	A	-	A	A	-	D	-	-	D	A	-	-	C	-	-	-	-	A	-	A	D	-	D	D	A	
Arsenic Acid	B	A	A	-	D	-	-	D	B	D	D	A	A	B	A	A	D	A	-	B	A	-	A	A	-	A	A	-	A	-	-	C	A
Asphalt	-	B	A	-	C	-	-	A	-	C	-	-	A	-	-	-	A	A	-	-	A	-	A	-	A	A	B	C	B	D	D	A	
Barium Carbonate	B	A	A	A	B	A	A	B	-	B	B	-	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	-	-	-	A
Barium Chloride	C	D	A	A	D	A	A	B	-	-	C	A	A	B	A	A	A	B	-	B	A	A	A	-	A	A	B	A	A	A	A	A	
Barium Cyanide	-	-	A	-	-	-	-	C	-	-	A	-	-	-	-	-	B	-	-	B	-	-	-	-	A	-	A	C	-	-	-	-	A
Barium Hydroxide	B	C	A	A	D	B	B	B	-	C	C	A	A	-	A	A	D	A	-	B	A	A	A	A	-	A	A	C	A	A	A	A	
Barium Nitrate	-	A	A	-	-	A	-	D	-	A	A	-	B	-	-	-	A	A	-	-	-	-	-	-	A	A	-	A	-	-	-	-	B
Barium Sulfate	B	A	A	A	D	A	A	C	-	C	A	A	-	A	A	A	A	-	B	A	A	A	B	-	A	A	D	A	A	A	-	-	B
Beet Sugar Liquids	A	A	A	-	A	-	-	A	B	A	-	-	A	-	-	A	B	A	B	-	A	-	-	A	-	A	A	-	B	A	A	A	
Benzaldehyde3																																	

	A = No effect B = Minor Effect C = Moderate D = Severe																																		
	302	304	316	440	Alum	Titanium	Hastelloy C	Bronze	Brass	Cast Iron	Carbon Steel	PVDF	PVC	Tygon	ETFE	Noryl	Polyacetal	Nylon	ABS	PE	PP	Ryton	Carbon	Ceramic	Ceramagnet	Viton	BUNA N	Silicon	Neoprene	EPDM	Rubber	Epoxy			
Calcium Hydroxide	B	A	A	-	C	A	A	B	-	-	-	-	A	A	A	A	B	A	-	B	A	-	A	A	A	A	A	C	A	A	A	A			
Calcium Hypochlorite	D	D	C	C	C	A	B	D	-	D	-	A	D	-	A	A	D	D	-	B	A	-	A	A	-	A	A	B	C	D	A	C	A		
Calcium Sulfate	B	A	A	A	B	A	B	B	-	-	-	A	A	A	A	A	A	A	C	B	A	A	A	A	-	A	A	-	D	-	C	A	A		
Calgon	-	A	A	-	-	-	-	C	-	D	-	-	-	-	-	A	B	-	-	-	A	-	A	A	-	A	A	-	A	-	-	-	A		
Cane Juice2	-	A	A	-	B	-	-	B	C	A	-	-	A	-	-	-	A	A	-	-	-	D	-	A	A	-	-	A	-	A	-	A	A		
Carbolic Acid (See Phenol)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
Carbon Bisulfide2	B	A	A	A	A	-	-	C	-	B	-	-	D	D	-	-	A	A	-	-	-	D	-	A	A	A	A	D	-	D	D	D	A		
Carbon Dioxide (wet)	-	A	A	-	C	-	A	C	C	C	-	-	-	-	A	-	-	-	-	-	-	-	-	A	A	-	-	-	-	-	-	-	-		
CarbonDisulfide2	-	B	A	-	C	-	-	C	C	B	C	-	D	C	A	D	A	A	-	D	D	A	A	B	-	A	D	-	D	D	D	D	A		
Carbon Monoxide	-	A	A	-	A	-	-	-	-	-	-	-	A	-	-	B	A	A	-	B	A	-	A	A	-	A	A	B	B	A	C	A	A		
Carbon Tetrachloride21	B	B	B	A	C	A	A	C	A	C	D	A	C	C	A	D	A	A	D	D	D	C	A	A	A	A	C	C	D	-	D	C	A		
Carbonated Water	B	A	A	A	A	-	-	B	-	D	-	-	A	-	-	A	A	A	-	-	-	-	A	A	-	A	A	-	A	-	A	-	A	A	
Carbonic Acid	B	A	B	A	A	-	A	B	-	D	-	A	A	-	A	A	A	A	-	B	A	-	A	A	-	A	B	B	A	A	A	A	A		
Catsup	-	A	A	A	D	-	-	C	-	D	-	-	A	-	-	A	B	A	B	-	A	-	A	A	-	A	A	-	C	-	-	-	A		
Chloracetic Acid2	D	D	D	D	C	A	A	D	-	D	-	D	A	D	A	-	D	D	-	D	D	-	A	A	-	D	D	-	D	B	D	B	B		
Chloric Acid	-	D	D	-	-	-	-	-	-	-	-	-	D	-	A	-	-	-	-	-	-	-	-	-	-	-	D	-	D	-	-	-	D		
Chlorinated Glue	-	A	A	-	D	-	-	C	-	D	-	-	-	-	C	-	C	D	-	-	-	-	-	-	-	A	C	-	D	B	D	A			
Chlorine, Anhydrous Liquid	-	D	D	D	D	A	A	D	-	C	-	-	D	B	A	A	D	D	-	D	D	C	A	D	-	A	D	-	D	B	D	B	B		
Chlorine (dry)	B	A	A	-	D	D	A	A	B	A	-	-	-	-	A	-	-	-	-	-	-	-	C	A	A	-	D	-	-	D	-	D	D		
Chlorine Water	D	-	D	-	D	A	B	D	D	D	-	A	A	-	A	C	-	D	-	-	D	C	C	A	-	A	D	C	D	-	-	-	-		
Chlorobenzene (Mono)	A	A	A	-	B	-	A	B	-	B	C	A	D	D	A	D	A	A	D	D	D	C	A	A	-	A	D	-	D	D	D	D	A		
Chloroform	A	A	A	A	D	A	A	B	-	D	C	C	D	C	A	D	A	C	D	D	D	C	A	A	A	A	D	D	D	D	D	D	A		
Chlorosulfonic Acid1	D	D	-	D	D	A	B	D	-	-	D	D	C	C	A	D	D	D	-	D	D	-	C	-	-	D	D	D	D	D	D	C	A		
Chlorox (Bleach)	-	A	A	-	C	-	A	A	-	D	C	-	A	B	A	A	D	D	B	-	D	C	A	A	-	A	C	-	B	B	D	A	A		
Chocolate Syrup	-	A	A	-	A	-	-	-	-	D	-	-	-	-	-	A	A	A	-	-	-	-	-	-	-	-	A	-	A	-	-	-	D	A	
Chromic Acid 5%	-	A	A	B	C	A	A	D	D	D	-	-	A	B	-	C	D	D	B	B	A	A	D	C	-	A	D	C	D	A	B	B	B		
Chromic Acid 10%	-	B	-	-	-	A	A	-	D	-	-	A	A	-	A	A	-	D	-	-	-	-	-	-	-	A	D	-	D	-	-	-	C		
Chromic Acid 30%	-	B	-	-	-	A	A	-	D	-	-	B	A	-	A	D	-	D	-	-	-	-	-	-	-	A	D	-	D	-	-	-	D		
Chromic Acid 50%	C	B	B	-	C	A	A	D	D	D	-	C	B	B	A	D	D	D	C	C	B	B	D	A	-	A	D	-	D	A	D	C	A		
Cider	-	A	A	A	B	-	-	A	-	D	-	-	A	-	-	A	B	-	-	B	-	-	-	-	-	A	A	-	A	-	-	-	A		
Citric Acid	-	A	A	A	C	A	A	D	C	D	-	A	A	-	A	A	B	C	C	B	B	-	A	A	B	A	D	C	A	A	A	A	A		
Citric Oils	-	A	A	-	C	-	-	B	-	-	-	-	-	-	-	A	B	-	-	-	-	-	-	-	-	A	A	C	D	-	-	-	A		
Coffee	A	A	A	A	A	-	-	B	-	C	-	-	-	-	A	A	A	A	-	-	-	-	-	-	-	-	A	-	A	-	-	-	A		
Copper Chloride	C	D	D	B	D	A	A	D	-	D	-	A	A	B	A	A	B	D	-	B	A	A	-	A	-	A	A	-	A	A	A	A	A		
Copper Cyanide	-	A	A	A	D	A	A	C	-	D	-	A	A	-	A	A	B	A	-	B	A	A	A	A	-	A	B	-	A	A	A	A	C		
Copper Floroborate	-	D	D	-	D	-	B	D	-	D	-	##	A	-	A	-	B	-	-	-	-	-	-	-	-	-	A	-	A	-	-	-	A		
Copper Nitrate	B	A	A	B	D	A	A	D	-	-	-	A	A	-	A	A	B	D	-	B	A	-	A	A	-	A	A	-	A	-	-	-	A		
Copper Sulfate (5% Sol)	-	A	A	A	D	A	A	D	D	D	-	-	A	-	A	A	B	D	-	B	A	A	A	A	-	A	A	C	A	-	-	-	A		
Copper Sulfate	B	B	-	-	-	A	A	C	D	-	-	A	A	-	A	A	-	C	-	-	-	-	-	-	-	B	B	-	A	A	-	-	A		
Cream	-	A	A	-	A	-	-	C	-	D	-	-	-	-	-	A	A	A	-	-	-	-	-	-	-	-	A	-	C	-	-	-	A		
Cresols2	-	A	A	-	B	-	-	D	C	-	-	-	D	D	-	-	D	-	D	D	C	A	A	A	-	D	D	D	D	D	D	A	A		
Cresylic Acid	B	A	A	-	C	A	B	C	-	-	-	B	B	D	A	-	D	D	-	C	-	-	-	-	-	A	D	-	D	D	D	A	A		
Cyclohexane	-	A	-	-	A	A	-	A	-	-	A	-	-	D	-	D	A	-	-	-	D	A	A	A	-	A	D	D	D	D	D	A	A		
Cyanic Acid	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	-	-	-	-	-	-	-	-	-	C	-	D	-	-	-	A		
Detergents	-	A	A	-	A	-	-	A	-	-	A	-	A	-	-	A	B	A	B	B	A	A	A	A	-	A	A	-	B	A	C	A	A		
Dichlorethane	-	A	A	-	-	-	A	-	-	-	-	-	D	D	A	-	-	A	-	-	-	-	-	-	-	B	-	-	D	-	-	-	A		
Diesel Fuel	A	A	A	-	A	-	-	A	-	A	A	-	-	-	-	D	A	-	-	-	-	-	-	-	-	A	A	-	A	-	-	-	-	A	
Diethylamine	A	A	-	-	A	-	-	A	-	-	-	-	D	-	A	B	D	-	-	-	-	C	-	A	A	-	D	B	-	B	B	C	A		
Diethylene Glycol	-	A	-	-	-	-	-	A	-	-	-	-	-	-	-	A	A	A	B	B	-	-	-	-	-	A	A	-	C	A	A	A	A		
Diphenyl Oxide	-	A	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A	D	-	D	D	D	A	A		
Dyes	-	A	A	-	B	-	-	C	-	-	-	-	-	-	-	A	A	-	-	-	-	-	-	-	-	-	-	C	-	-	-	-	A		
Epsom Salts																																			
(Magnesium Sulfate)	B	A	A	A	A	A	B	B	-	-	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	A	A	-	A	-	-	-	C	A	
Ethane	A	A	-	-	A	-	-	A	-	-	-	-	-	-	-	D	A	-	-	-	-	-	-	-	-	A	A	-	A	-	-	-	-	A	
Ethanolamine	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	D	-	-	-	-	-	-	-	-	-	A	A	-	D	B	C	B	-	C	A
Ether3	A	A	A	A	A	-	B	B	A	-	B	-	D	C	-	D	A	C	-	-	-	-	-	-	-	A	A	A	C	D	-	D	C	D	A
Ethyl Acetate2	-	A	A	-	B	-	B	B	-	-	C	D	D	D	A	D	A	A	D	C	C	A	A	A	-	D	D	C	D	B	D	A	A		
Ethyl Chloride	-	A	A	A	B	A	B	B	-	C	D	A	D	D	A	D	A	A	-	D	D	A	A	A	-	A	D	D	C	A	A	A	A		
Ethyl Sulphate	-	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	B	-	-	-	-	-	-	-	-	A	A	-	-	-	-	-	-	A	
Ethylene Chloride2	-	A	A	-	C	B	B	A	-	C	C	-	D	-	A	D	A	-	D	-	D	A	A	A	-	A	D	D	D	C	D	A	A		
Ethylene Dichloride	-	A	A	-	D	A	B	C	-	-	C	-	D	D	A	D	A	A	-	D	A	A	C	A	-	A	D	D	D	C	D	A	A		
Ethylene Glycol4	-	A	A	-	A	-	A	B	B	B	C	A	A	B	A	A	A	A	B	B	A	A	A	A	-	A	A	A	A	C	A	A	A	A	
Ethylene Oxide	-	-	A	-	A	-	-	A	-	-	-	-	D	-	A	A	A	A	-	-	-	-	-	-	-	-	D	D	D	D	C	D	A		
Fatty Acids	-	A	A	-	B	A	A	C	-	D	-	-	A	B	A	B	A	A	-	B	A	-	-	-	-	-	A	C	C	B	C	C	A		
Ferric Acid	-	D	D	D	D	A	B	D	D	D	-	A	A	B	A	A	B	D	-	B	A	A	A	A	-	A	D	C	C	B	A	A	A		
Ferric Nitrate	-	A	A	A	D	A	A	D	-	-	-	A	A	-	A	A	B	D	-	B	A	A	A	A	-	A	D	A	A	A	A	A	A	A	
Ferric Sulfate	-	A	C	A	D	A	A	D	D	D	-	A	A	B	A	A	B	A	C	-	-	-	-	-	-	A	B	C	A	-	-	-	A	A	

	302	304	316	440	Alum	Titanium	Hastelloy C	Bronze	Brass	Cast Iron	Carbon Steel	PVDF	PVC	Tygon	ETFE	Noryl	Polyacetal	Nylon	ABS	PE	PP	Ryton	Carbon	Ceramic	Ceramagnet	Viton	BUNA N	Silicon	Neoprene	EPDM	Rubber	Epoxy				
Grease4	A	A	A	-	A	-	-	B	-	A	A	-	-	-	A	-	A	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	A			
Heptane1	A	-	A	-	A	-	A	A	-	-	B	A	A	-	A	D	A	A	A	C	D	D	A	A	A	-	A	A	-	B	D	-	A			
Hexane1	A	A	A	-	A	-	A	B	-	-	B	A	A	C	-	A	D	A	A	D	-	C	A	A	A	-	A	A	B	B	D	D	A			
Honey	-	A	A	-	A	-	-	A	-	A	-	-	A	-	-	A	A	A	A	B	-	A	-	A	A	-	A	A	-	A	A	-	A			
Hydraulic Oils (Petroleum)1	A	A	A	-	A	-	-	B	-	A	A	-	-	-	A	-	A	A	-	-	D	-	A	A	-	A	A	-	B	D	D	A				
Hydraulic Oils (Synthetic)1	-	A	A	-	A	-	-	A	-	A	-	-	-	-	-	-	A	A	-	-	D	-	A	A	-	A	C	D	-	-	-	A				
Hydrazine	-	A	A	-	-	-	-	-	-	C	-	-	-	-	-	-	D	-	-	-	-	-	-	A	-	-	A	B	D	B	A	C	A			
Hydrobromic Acid 20%	-	-	D	-	-	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	A	-	-	B	-	A	D	-	C	-	-	B				
Hydrobromic Acid4	D	D	D	D	D	A	A	D	-	D	D	A	A	B	A	C	D	D	-	B	B	-	A	A	-	A	D	D	D	A	A	A				
Hydrochloric Acid(Dry Gas)	D	C	A	-	D	-	A	-	-	-	D	-	A	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A			
Hydrochloric Acid 20%4	-	D	D	D	D	C	B	D	-	D	-	A	A	B	A	A	D	D	B	A	A	D	A	A	D	A	C	-	C	A	C	A				
Hydrochloric Acid 37%4	-	D	D	D	D	C	B	D	-	D	-	A	A	B	A	A	D	D	C	A	A	D	A	C	D	A	C	C	C	C	D	A				
Hydrochloric Acid 100%	-	D	D	-	D	D	C	D	-	D	-	-	A	A	A	-	-	D	-	A	-	-	A	C	-	C	D	-	C	-	-	A	A			
Hydrocyanic Acid	A	A	A	C	A	A	A	D	D	-	C	-	A	B	A	A	B	A	-	B	A	-	A	A	-	A	C	-	C	-	-	-	A			
Hydrocyanic Acid(Gas 10%)	-	D	D	-	-	-	-	-	-	-	-	-	A	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A			
Hydrofluoric Acid 20%1	-	D	D	D	D	D	B	D	-	D	-	-	D	B	A	A	D	D	-	C	A	C	B	C	D	A	D	-	C	A	C	B				
Hydrofluoric Acid 75%12	-	C	D	-	D	D	C	D	-	D	-	A	C	B	A	A	D	D	-	C	B	C	D	D	D	A	D	D	D	C	C	C				
Hydrofluoric Acid 100%	D	D	D	-	D	D	B	D	-	D	D	-	C	D	A	-	-	-	-	D	-	C	D	D	-	D	-	D	-	-	-	D	A			
Hydrofluosilicic Acid 20%	-	D	D	-	D	D	B	A	-	D	-	-	D	-	A	B	D	D	-	-	A	-	A	D	-	A	B	-	B	A	A	C				
Hydrofluosilicic Acid	-	D	D	-	C	-	C	D	-	-	-	-	C	A	-	-	-	-	-	-	-	-	-	A	-	-	-	D	A	-	-	-				
Hydrogen Gas	A	A	A	-	A	-	-	A	-	B	B	A	A	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A			
Hydrogen Peroxide 10%	-	C	C	-	A	C	A	D	D	D	-	-	A	A	A	-	-	D	-	A	-	B	A	A	-	-	A	-	D	-	-	C	D			
Hydrogen Peroxide 30%	-	-	B	-	-	B	A	D	-	D	-	-	A	-	A	-	D	-	D	-	A	C	-	-	-	A	D	-	C	-	-	B				
Hydrogen Peroxide	-	A	B	A	A	B	A	D	D	D	C	A	C	A	B	D	D	-	B	A	C	-	A	A	A	D	C	D	C	C	A	A				
Hydrogen Sulfide, Aqueous Solution	-	D	A	C	C	A	A	D	C	D	-	A	A	B	A	A	D	D	-	B	A	A	A	A	D	C	-	B	A	D	A	A				
Hydrogen Sulfide (dry)	A	C	A	-	D	-	A	D	C	B	B	-	A	-	A	-	-	D	-	-	-	-	A	-	A	-	D	-	-	-	-	A	A			
Hydroxyacetic Acid (70%)	-	-	-	-	D	B	-	-	-	-	-	-	A	-	-	-	D	-	-	-	-	-	A	A	-	A	A	-	A	A	-	-	A			
Ink	A	A	A	-	C	-	-	C	-	D	D	-	-	-	-	B	A	A	-	B	-	-	-	A	A	A	A	-	A	-	-	-	-	A		
Iodine	-	D	D	D	D	A	B	D	-	D	-	-	D	B	A	A	C	D	D	D	D	-	D	A	-	A	B	-	D	B	D	A				
Iodine (in Alcohol)	-	-	B	-	-	D	A	-	-	-	-	-	D	-	A	C	-	D	-	-	B	-	-	A	-	A	D	-	D	-	-	-				
Iodoform	B	C	A	-	A	-	-	C	-	C	B	-	-	-	A	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-			
Isotane2	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	D	A	-	-	-	D	-	-	A	-	A	A	-	-	-	-	-	D	A		
Isopropyl Acetate	-	-	B	-	C	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	A	-	D	D	-	D	B	D	A			
Isopropyl Ether2	A	-	A	-	A	-	-	A	-	-	A	-	-	-	A	D	A	-	-	D	-	-	-	A	A	-	D	B	-	D	D	-	-			
Jet Fuel (JP#, JP4, JP5)	A	A	A	-	A	-	-	A	-	-	A	A	A	-	A	D	A	A	A	-	-	D	A	A	A	-	A	A	D	D	D	D	A			
Kerosene2	A	A	A	A	A	A	A	A	A	A	B	A	A	D	A	D	A	A	B	D	D	A	A	A	A	A	A	D	D	A	D	A	A			
Ketones	A	A	A	-	B	A	A	A	-	A	A	D	D	A	D	B	A	-	D	D	A	C	A	-	D	D	-	D	D	D	C	C	C			
Lacquers	A	A	A	-	A	-	-	A	C	C	C	-	-	D	-	C	A	A	-	-	A	-	-	A	A	-	D	D	-	D	-	-	D	A		
Lacquer Thinners	-	-	A	-	-	A	A	-	C	-	-	-	C	-	A	D	-	A	-	-	B	-	-	A	-	-	D	-	D	A	-	-	-			
Lactic Acid	A	A	B	C	C	A	A	D	-	D	D	C	A	B	A	A	B	C	-	B	A	A	A	A	-	B	B	-	A	B	A	A	A			
Lard	B	A	A	A	A	-	-	A	-	A	C	-	A	-	-	-	A	A	C	-	A	-	-	A	A	-	A	A	C	B	-	-	-	D	A	
Latex	-	A	A	-	A	-	-	A	-	-	-	-	-	-	-	A	A	A	-	B	-	-	-	A	-	A	A	-	C	A	-	-	-	A		
Lead Acetate	B	A	A	-	D	A	A	C	-	-	D	-	A	B	A	A	A	A	-	B	A	-	-	A	A	-	D	B	-	D	A	A	A			
Lead Sulfamate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	A	-	-	-	-	-	-	A	B	C	A	D	C	A			
Ligroin3	-	-	A	-	-	-	-	A	-	-	-	-	-	-	-	D	A	-	-	-	D	-	-	A	-	A	A	-	B	A	D	A	A			
Lime	-	A	A	-	C	A	A	-	A	-	A	-	A	-	-	A	D	-	C	-	-	-	-	A	A	-	A	A	C	B	D	-	-	A		
Lubricants	-	A	A	-	A	A	A	B	-	-	-	-	A	-	A	-	A	A	B	-	A	A	A	A	-	A	A	C	D	-	-	-	-	D	A	
Magnesium Carbonate	-	A	A	A	-	-	B	-	-	-	-	-	A	-	-	A	A	-	-	B	A	-	-	A	-	-	A	-	A	A	-	-	-	A		
Magnesium Chloride	B	B	B	A	D	A	A	B	C	D	C	-	A	B	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	A	-	-	-	A	A	
Magnesium Hydroxide	A	A	A	-	D	A	A	C	B	B	B	A	A	-	A	A	A	A	-	B	A	-	A	A	-	A	B	-	B	-	-	-	C	A		
Magnesium Nitrate	-	A	A	A	-	A	A	-	-	-	-	-	A	-	A	A	A	A	-	B	A	-	-	A	-	A	A	-	A	-	-	-	-	A		
Magnesium Oxide	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	A	-	A	-	-	-	-	A		
Magnesium Sulfate	B	B	A	-	B	A	B	B	B	C	B	-	A	B	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	-	-	-	-	A	A	
Maleic Acid	C	A	A	A	B	A	A	C	-	-	B	-	A	B	A	A	C	A	-	-	C	-	-	A	A	-	A	D	-	A	D	D	A			
Maleic Anhydride	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	C	-	-	-	-	-	-	A	A	-	A	D	-	D	-	-	-	D	A	
Malic Acid	B	A	A	-	C	-	A	D	-	-	D	-	A	-	A	-	-	A	-	-	-	-	-	-	A	-	B	-	-	-	-	-	-	A		
Mash	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	-	A	A	-	-	-	-	-	-	A	A	-	A	-	-	-	-	-	-	A	
Mayonnaise	A	A	A	-	D	-	-	D	-	D	D	-	-	-	A	A	A	A	B	-	A	-	-	A	A	-	A	A	-	-	-	-	-	-	A	
Melamine	-	D	D	-	-	-	-	D	-	-	-	-	-	-	-	-	D	-	-	-	-	-	-	A	A	-	C	-	-	-	-	-	-	-	A	
Mercuric Chloride (Dilute Solution)	D	D	D	D	D	A	B	D	D	D	D	-	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	A	-	-	-	-	A	A
Mercuric Cyanide	A	A	A	-	D	A	A	D	-	D	-	-	A	-	A	A	A	-	-	B	A	-	-	A	A	-	A	-	-	-	-	-	-	-	-	A
Mercury	A	A	A	A	C	C	A	D	D	A	A	-	A	-	A	A	A	A	-	B	A	-	-	A	A	-	A	-	-	-	-	-	-	-	A	A
Methyl Acetone	A	-	A	-	A	-	-	A	-	A	A	-	-	-	A	D	A	-	-	-	-	-	-	-	-	-	D	D	-	D	-	-	-	-	-	C
Methyl Alcohol 10%	A	-	A	-	C	-	A	C	-	-	B	-	A	-	A	-	-	A	-	-	-	-	-	-	-	-	-	B	-	-	-	-	-	-	-	A
Methyl Bromide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	D	-	-	-	A	A	-</										

	A = No effect B = Minor Effect C = Moderate D = Severe			302	304	316	440	Alum	Titanium	Hastelloy C	Bronze	Brass	Cast Iron	Carbon Steel	PVDF	PVC	Tygon	ETFE	Noryl	Polyacetal	Nylon	ABS	PE	PP	Ryton	Carbon	Ceramic	Ceramagnet	Viton	BUNA N	Silicon	Neoprene	EPDM	Rubber	Epoxy				
Cinnamon	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	A	-	-	A	-	A	A	-	D	-	-	D	-	-	A				
Citric	-	A	A	-	-	-	-	-	-	D	-	D	-	-	-	-	-	-	-	A	A	-	-	-	-	A	A	A	-	A	A	-	D	-	-	A			
Clove	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	-	B	-	A	A	-	-	A	-	-	-	-	-	A			
Coconut	-	A	A	-	B	-	-	-	-	A	-	A	-	-	-	-	-	-	-	A	A	-	-	A	-	A	A	-	A	A	-	A	A	D	A	A			
Cod Liver	-	A	A	-	B	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	C	-	A	-	A	A	-	A	A	-	B	A	D	A	A			
Corn	-	A	A	A	B	-	-	-	-	B	-	A	-	-	-	-	-	-	-	A	A	C	-	A	-	A	A	-	A	A	-	D	C	D	A	A			
Cotton Seed	B	A	A	A	B	-	-	-	-	B	-	A	C	-	A	-	-	-	-	A	A	C	-	A	-	A	A	-	A	A	-	D	C	D	A	A			
Cresote2	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	-	-	-	D	-	A	A	-	A	A	-	B	D	D	A	A			
Diesel Fuel (2D, 3D, 4D, 5D)	-	A	A	-	A	-	-	-	-	A	-	-	-	-	-	-	-	-	-	D	A	A	-	-	A	A	A	-	A	A	-	D	D	D	A	A			
Fuel (1,2,3,5A, 5B, 6)	-	A	A	-	A	A	A	A	A	A	-	-	-	-	-	-	-	-	-	A	D	A	-	-	B	-	A	A	-	A	B	-	D	D	D	A	A		
Ginger	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	A	-	D	-	-	-	A			
Lemon	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	D	-	A	A	-	A	-	A	-	D	-	-	A			
Linseed	-	A	A	A	A	-	-	-	-	A	-	A	-	-	-	-	-	-	-	A	A	C	-	A	-	A	A	A	-	A	A	-	D	D	D	A	A		
Mineral	A	A	A	A	A	-	-	-	-	A	-	A	B	-	A	-	-	-	B	A	A	-	-	B	-	A	A	A	-	A	A	-	B	D	D	A	A		
Olive	A	A	A	-	A	-	-	-	-	B	-	A	B	-	A	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A	A	C	B	-	D	A	A		
Orange	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	A	-	-	A	-	A	A	-	A	A	-	D	-	-	-	A		
Palm	-	A	A	-	A	-	-	-	-	B	-	-	-	-	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	-	A			
Peanut3	-	A	A	-	A	-	-	-	-	A	-	A	-	-	-	-	-	-	-	A	-	-	-	D	-	A	A	-	A	A	-	D	-	-	D	A	A		
Peppermint2	-	A	A	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	A	-	-	-	D	-	A	A	-	A	D	-	D	-	-	-	A			
Pine	A	A	A	-	A	-	-	-	-	D	-	C	B	-	A	-	-	-	-	A	-	A	-	-	-	-	A	A	-	A	A	-	D	-	D	A	A		
Rape Seed	-	A	A	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	B	-	D	-	D	A	A		
Rosin	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	-	A	-	A	A	-	A	A	-	-	-	-	-	-	A		
Sesame Seed	-	A	A	-	A	-	-	-	-	A	-	A	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	D	-	-	-	A		
Silicone	-	A	A	-	-	-	-	-	-	A	-	A	-	-	-	-	-	-	-	A	A	A	-	-	A	-	A	A	A	-	A	A	-	A	-	-	A	A	
Soybean	-	A	A	-	A	-	-	-	-	B	-	A	-	-	-	-	-	-	-	A	A	-	-	A	-	A	A	-	A	A	-	D	-	-	D	A	A		
Sperm	-	A	A	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	D	-	-	-	A		
Tanning	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	D	-	-	-	A		
Turbine	-	A	A	-	A	-	-	-	-	A	-	A	-	-	-	-	-	-	-	A	-	C	-	-	-	-	A	A	-	A	A	-	D	-	-	D	A		
Oleic Acid	B	A	A	B	B	-	B	B	C	C	C	-	A	C	A	C	B	A	B	D	C	-	-	-	-	A	A	-	D	B	D	D	D	D	D	A	A		
Oleum 25%	-	-	-	-	-	-	-	-	-	A	-	-	-	B	D	-	A	D	-	-	-	-	-	-	-	-	A	-	A	D	D	D	D	D	-	D			
Oleum	B	-	A	-	B	-	-	-	-	C	C	-	B	D	D	-	-	-	-	A	-	D	-	-	D	-	-	A	-	A	C	D	D	D	D	A	A		
Oxalic Acid (Cold)	C	A	B	A	C	C	B	B	C	D	D	-	A	B	A	C	C	D	-	-	A	A	-	-	-	A	A	-	A	B	C	B	A	D	C	A	A		
Paraffin	A	A	A	A	A	-	-	-	-	A	-	B	B	A	A	-	-	-	-	A	B	A	A	B	-	A	-	A	A	-	A	A	-	-	-	-	-	A	
Pentane	A	C	C	-	A	-	B	A	-	B	B	-	-	-	-	-	-	-	-	A	D	A	A	D	-	-	A	A	-	A	A	-	B	D	D	A	A		
Perchloroethylene2	B	A	A	-	A	-	-	-	-	C	-	B	B	A	-	-	-	-	-	A	D	A	-	-	D	-	A	A	-	A	C	D	D	D	D	A	A		
Petrolatum	A	-	A	-	B	-	-	-	-	B	-	C	C	-	-	-	-	-	-	A	D	A	A	B	-	-	-	A	A	-	A	A	-	B	A	D	A	A	
Phenol 10%	B	A	A	-	A	-	B	C	-	B	D	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	B	D	-	C	D	C	C	A			
Phenol (Carbolic Acid)	B	A	A	A	B	C	A	B	D	D	D	A	A	C	A	C	D	D	-	-	D	B	A	A	D	A	A	D	A	D	-	D	D	D	B	B			
Phosphoric Acid (to 40% Solution)	-	B	A	A	D	A	A	D	D	D	-	-	-	-	-	-	-	-	-	A	B	A	A	D	D	C	B	A	A	B	C	D	A	D	-	D	B	C	A
Phosphoric Acid (40-100% Solution)	-	C	B	B	D	B	A	D	D	D	-	-	-	-	-	-	-	-	-	A	B	A	A	D	D	C	A	A	B	D	D	A	D	-	D	B	C	C	
Phosphoric Acid (Crude)	-	D	C	C	D	C	A	D	D	D	A	-	-	-	-	-	-	-	-	A	D	D	D	C	-	A	C	D	-	A	D	-	D	B	-	-	A		
Phosphoric Anhydride (Dry or Moist)	-	A	A	-	-	-	-	-	-	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	D	-	D	-	-	-	A	-	
Phosphoric Anhydride (Molten)	-	A	A	-	D	-	-	-	-	D	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	C	-	D	-	-	-	A	-	
Photographic (Developer)	-	C	A	C	C	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	C	-	-	B	A	-	A	A	-	A	A	-	A	-	-	-	-	A	
Phthalic Anhydride	B	A	B	-	B	-	A	B	-	C	C	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	C	-	-	-	-	-	-		
Picric Acid	B	A	A	-	C	-	A	D	D	D	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	D	A	-	-	-	A	A	
Plating Solutions																																							
Antimony Plating 130°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	D	-	-	A	-	-	A	-	A	A	D	A	-	-	-	B	
Arsenic Plating 110°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	-	C	-	A	A	D	A	-	-	-	B		
Brass Plating																																							
Regular Brass Bath 100°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	C	-	A	A	D	A	-	-	-	-	B		
High Speed Brass Bath 110°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	D	-	A	A	D	A	-	-	-	-	B		
Bronze Plating																																							
Copper-Cadmium Bronze Bath R.T.	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	C	-	A	A	D	A	-	-	-	-	B		
Copper-Tin Bronze Bath 160°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	D	-	A	A	D	B	-	-	-	-	C		
Copper-Zinc Bronze Bath 100°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	C	-	A	A	-	A	-	-	-	-	B		
Cadmium Plating																																							
Cyanide Bath 90°F	-	-	A	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	A	-	-	C	-	A	A	-	A	-	-	-	-	B		
Fluoborate Bath 100°F	-	-	A	-	-	D	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	D	-	-	D	-	A	B	-	C	-	-	-	-	B		
Chromium Plating																																							
Chromic-Sulfuric Bath 130°F	-	-	C	-	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	-	A	D	-	D	-	-	A	-	C	D	-	D	-	-	-	-	D		
Fluosilicate Bath 95°F	-	-	C	-	-	C	A																																

	A = No effect B = Minor Effect C = Moderate D = Severe																																			
	302	304	316	440	Alum	Titanium	Hastelloy C	Bronze	Brass	Cast Iron	Carbon Steel	PVDF	PVC	Tygon	ETFE	Noryl	Polyacetal	Nylon	ABS	PE	PP	Ryton	Carbon	Ceramic	Ceramagnet	Viton	BUNA N	Silicon	Neoprene	EPDM	Rubber	Epoxy				
Tallow	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	A	A	A	-	C	-	-	A	A	-	A	A	-	-	-	-	-	A			
Tannic Acid	B	A	A	A	C	A	B	B	-	C	C	A	A	B	A	A	B	D	-	B	A	-	A	A	A	A	A	D	C	A	A	A	A			
Tanning Liquors	-	A	A	-	C	A	A	-	-	-	-	-	A	B	A	-	B	-	-	-	A	-	A	A	-	A	C	-	-	-	-	-	A			
Tartaric Acid	B	A	B	B	C	A	B	A	C	D	D	A	A	B	A	A	B	A	-	B	A	-	A	A	-	A	D	C	A	-	-	A	A			
Tetrachlorethane	-	-	A	-	-	A	A	-	-	-	-	-	D	-	A	D	A	A	-	-	A	-	A	A	-	A	D	-	-	-	D	D	A			
Tetrahydrofuran	-	A	A	-	D	-	-	D	-	D	A	D	D	-	A	D	A	A	-	D	C	A	A	A	-	D	D	-	D	B	D	A	A			
Toluene, Toluol3	A	A	A	-	A	A	A	A	A	A	A	A	D	D	A	D	A	A	D	D	D	A	A	A	A	C	D	D	D	D	D	D	A			
Tomato Juice	A	A	A	-	A	-	-	C	-	C	C	-	-	-	A	A	B	A	B	-	A	A	A	A	-	A	A	-	A	-	-	-	A			
Trichlorethane	-	C	A	-	C	A	A	C	-	C	-	-	-	-	A	D	A	-	-	-	-	-	A	A	-	A	D	D	D	D	D	A				
Trichlorethylene2	B	A	A	-	B	A	A	B	A	C	B	A	D	-	A	D	A	C	D	D	D	C	A	A	C	A	D	D	D	D	D	A				
Trichloropropane	-	-	A	-	-	-	-	A	-	-	-	-	-	-	-	D	A	-	D	-	-	-	A	A	-	A	A	-	A	-	-	-	A			
Tricresylphosphate	-	-	A	-	-	B	A	A	-	-	-	-	D	-	A	A	C	-	-	-	-	-	A	A	-	B	D	-	D	A	-	-	A			
Triethylamine	-	-	-	-	-	-	-	A	-	-	-	-	A	-	-	B	D	-	-	-	-	-	A	A	-	A	A	D	B	-	-	-	A			
Turpentine3	B	A	A	-	C	-	A	B	C	B	B	A	A	B	A	D	A	A	-	D	B	A	A	A	-	A	D	-	D	D	D	A	A			
Urine	-	A	A	-	B	-	-	C	-	B	-	-	A	-	-	A	A	A	-	B	A	-	A	A	-	A	A	-	D	A	-	-	-	A		
Vegetable Juice	-	A	A	-	A	-	-	C	-	D	-	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	A	B	D	-	-	-	A			
Vinegar	A	A	A	A	D	A	A	B	B	C	D	A	A	-	A	A	B	A	B	B	C	-	B	A	C	A	A	-	-	-	-	-	-	A		
Varnish	A	A	A	A	A	-	-	A	B	-	C	-	-	-	A	D	A	A	-	-	A	-	A	A	A	A	B	C	D	-	-	-	-	A		
Water, Acid, Mine	-	A	A	-	C	-	-	C	D	C	-	-	A	B	-	A	D	A	B	-	A	B	A	A	-	A	A	-	B	-	-	-	-	A		
Water, Distilled, Lab Grade 7	-	A	A	-	B	-	-	A	-	D	-	-	A	B	A	A	A	A	A	-	A	A	A	A	A	A	A	A	-	B	A	A	A	A		
Water, Fresh	A	A	A	-	A	-	-	A	C	B	D	-	A	B	A	A	A	A	A	D	A	A	A	A	A	A	A	A	-	B	A	A	A	A		
Water, Salt	-	A	A	-	B	-	-	B	C	D	-	-	A	B	-	A	A	A	-	-	A	A	A	A	A	A	A	-	B	A	A	A	A			
Weed Killers	-	A	A	-	C	-	-	C	-	-	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	A	B	-	C	-	-	-	-	A		
Whey	-	A	A	-	B	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	-	-	-	-	-	-	A	
Whiskey & Wines	A	A	A	A	D	-	-	B	B	D	D	-	A	-	A	A	A	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	A	A		
White Liquor (Pulp Mill)	-	A	A	-	-	-	A	D	-	C	-	-	A	-	A	A	D	A	-	-	A	-	A	A	-	A	A	-	A	-	-	-	-	-	A	
White Water (Paper Mill)	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	B	A	-	-	A	-	-	A	A	-	A	-	-	-	-	-	-	-	-	A	
Xylene2	A	A	A	-	A	-	A	A	A	A	B	A	D	-	A	D	A	A	D	D	D	A	A	A	A	A	D	D	D	D	D	D	D	A	A	
Zinc Chloride	D	D	B	B	D	A	B	D	D	D	D	A	A	-	A	A	C	A	-	B	A	-	A	A	A	-	A	A	-	A	A	A	A	A	A	
Zinc Hydrosulphite	-	-	A	-	D	-	-	D	-	D	-	-	-	-	-	A	C	-	-	-	-	-	A	A	A	-	-	-	-	-	-	-	-	-	-	A
Zinc Sulfate	B	A	A	A	D	A	B	B	C	C	D	A	C	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	C	A	A	A	A	